# **Metamark MD-FL440**

## 440gsm PVC Event Banner Print Media



### **Product Description**

Metamark MD-FL440 is a 440gsm laminated and reinforced PVC banner, suitable for short term promotion and event banners. It has a satin surface and can be used for exterior or interior applications. The product is fire retardant in accordance with DIN 75200 to suit interior applications. For use on Solvent, UV, and Latex printers. It should be printed on the smooth side. A slitting service is not available on this product.

#### **Features & Benefits**

- For Solvent, Eco Solvent, UV and Latex (300,500,700,800)
- One part system.

- Fire retardant in accordance with DIN 75200.
- Used to produce high quality prints.

Face Film		Finishes		
Base Fabric Type of Coating Weight	Polyester PVC 440gsm	Finishes Available	MD-FL440	White Satin
Weight Tensile strength	670 / 610 N/5cm (warp/weft)	Durability		
Tear Strength Cold Resistance Heat Resistance	95/85 N/5cm (warp/weft) -30℃ +70°C	Shelf Life External weathering	1 year. (10-20°C and 50% R.H). <1 year (unprinted). This refers to the unprinted vinyl when installed. Refer to ink manufacturer for durability of the	
Roll Presentation		Fire Rating	finished product.  Fire retardant in accordance with DIN	
Roll Widths Roll Lengths	0.76m / 1.067m / 1.37m / 1.6m 30m	— The nating	75200, <100mm / min performance requirements Regulations REACH Compliant.	
SuperWide Rolls Presentation	3.2m x 50m Face film outward	Regulations		

## **Printing and Handling**

- Always perform a test print first. Ensure that the correct profiles and heater settings are used. Refer to www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- To be printed on the smooth side, so load material accordingly.
- The weight of the banner may necessitate some slack on the unwind.
- The product is designed to be used without an overlaminate. If a liquid laminate is used it is the responsibility of the user to test.
- The durability of the finished print is dependent on the inks and printer.

## MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.