

Metamark MD-MX

Heat Transfer Flex for Textiles



Product Description

MD-MX is a high quality heat transfer flex that has been developed for 'print and cut' use on solvent inkjet printers. It is suitable for promotional T shirts, sportswear and workwear. The high-quality polyurethane film has a matt, reflection-free surface laminated with a thermally activated adhesive. It can be applied to cotton and polyester / acrylic blend fabrics. It benefits from being highly flexible, and with its low tack self adhesive liner allows easier cutting and weeding.

Features & Benefits

- Suitable promotional T-Shirts, sportswear and workwear.
- For use on Solvent and Eco Solvent prints.
- PVC, Phthalate and Chlorine Free.
- Can be applied to cotton and polyester / acrylic blend fabrics.

Specifications

Face Film	Polyurethane
Adhesive	Hot Melt
Thickness	100 micron
Liner	Self-adhesive
Regulations	REACH Compliant

Heat Press Settings

Temperature	155°C - 165°C
Time	17 - 20 sec
Pressure	Medium

Release Liner

Print	Unprinted
Weight	90gsm nominal

Washing and Care Instructions

The product is machine washable 40°C. Test a sample print first as some printers can achieve lower abrasion resistance. Wash inside out. Use mild colour safe detergents.

Troubleshooting

Edge Curling: Allow 24 hours before cutting, when cutting flush to the print. Use MX Application Tape to lift.
Difficulty Weeding: Ensure material is cooled to room temperature before weeding.
Difficulty lifting film: Lift graphics face down with MX tape.
Weak colours on Roland Printers: Set Colour Management setting in RIP to 'Max Impact', on a MD5 profile.
Poor abrasion resistance when washing: Allow 24 hours after printing and before pressing for inks to dry. Wash inside out.

Handling and Printing

- Suitable for use on Solvent and Eco Solvent inkjet printers. Always perform a test print first.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.
- Allow 24 hours after printing before cutting, and before pressing. Failure to do so can cause the heat press to pre-cure the inks and will result in low abrasion resistance when washing.
- Ensure that the correct profile is used. Most profiles are available and can be downloaded from www.metamark.co.uk.
- Ensure that the correct heater settings are used.
- Not suitable for use on 100% Nylon or Polyester as the colour of the garment may bleed through.

Application

- Print and cut the image, orientated the correct way round. Always perform a test first.
- Once weeded, apply MX application tape to lift the print. The product can be applied to the textile using a heat transfer press, applying pressure through the application tape.
- Press first for 8-10 seconds, remove the application tape, then covering the image with a silicone-release paper and pressing for 17 sec. Please note that these guidelines may vary.

PVC Free

This product contains no plasticisers, phthalates or chlorine.

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

- Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387132
- Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk
www.metamark.co.uk