

Metamark MD-CV2

Premium Clear Vision (Perforated One-Way Film)



Product Description

Metamark MD-CV2 is a premium grade perforated one-way vision film, supplied on a multi-layer release liner to offer improved print performance on Solvent, Eco Solvent, Latex and UV printers. It has 40% open area and 1.6mm perforations. It is suitable for advertising applications on vehicles and buildings, maintaining visibility from the inside. The black/white laminate has a clear adhesive to maintain full visibility through the holes and to ensure clean removal up to 6 months after application (Not recommended for application to polycarbonate). It can be applied on lightly curved surfaces like some rear windows of cars but it is not aimed to be deformed in 3D. The experience and the dexterity of the applier will be decisive for the end result. Overlaminating is recommended to maintain visibility in wet weather.

Material Handling

- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

Printing and Overlaminating

- Suitable for use on Solvent, Eco Solvent, UV and Latex inkjet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Allow 24-48 hours after printing and before application or overlaminating.
- Apply the overlaminate before applying to the window. Apply the product dry to the window. Ensure the laminate overlaps the Clear Vision (Recommended overlap 10mm).
- On flat glass use MetaGuard 620 optically clear laminate. On glass with double curvature use MetaGuard 670 cast laminate. For U.V prints the user should determine a suitable overlaminate.

Notes:

- Overlaminating can cause optical imperfections due to the uneven entrapment of air under the film, which is unavoidable.
- Extra care should be taken when applying to cold glass where initial tack will be low, and where the film is heavily printed, as retained solvents from the printing process affect the media.
- On vehicles do not apply to the front side windows or windscreen. Refer to the legislation in the country in which it is being used before installation. In the UK, Road Vehicle Regulation 33 states that if visibility is restricted to the rear mirror then two side mirrors must be correctly fitted and functional. In so far as the product is interpreted as window tinting film then it is covered by Regulation 32, whereby the rear side and rear windows are exempt under ECE Directive.
- There has to be a gap between the end of the film and the surrounding of the window. Never apply the film onto the sealing. Application to the window frame may cause the self-adhesive film to become detached. Leave a distance of at least 5 mm to the window frame.

Face Film

Face Film	White PVC
Gauge	145 micron nominal
Perforation size	1.6mm hole, 40% Open Area
Dimensional stability	Good

Adhesive

Type	Removable solvent based acrylic. Can be removed cleanly for up to 6 months.
Application temperature	+12°C to +32°C
Service temperature	-17°C to +50°C
Adhesion to glass 8 mins	10.3N/5mm nominal
Adhesion to glass 24 hour	11.85N/5mm nominal

Release Liner

Weight	135gsm Multi-layer Kraft Paper
--------	--------------------------------

Finishes

Finish Available	MD-CV2
------------------	--------

Roll Presentation

Roll sizes and net weights	760mm x 50m	11kg
	1370mm x 50m	20kg
	1520mm x 50m	22kg
Presentation	Face film outwards.	

Durability

Shelf Life	1 year
Fire Rating	M1 and B1 certified
External weathering	2 years unprinted. Refer to ink manufacturer for durability of the finished product.
Regulations	REACH compliant

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. **Please Note:** The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

○ Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140 • Fax +44 (0)1524 387147
○ Metamark House • Octimum Business Park • Forsyth Road • Woking • GU21 5SF • Tel +44 (0)1483 571111 • Fax +44 (0)1483 570540

sales@metamark.co.uk
www.metamark.co.uk

Metamark (UK) Limited

○ Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140 • Fax +44 (0)1524 387147

○ Metamark House • Octimum Business Park • Forsyth Road • Woking • GU21 5SF • Tel +44 (0)1483 571111 • Fax +44 (0)1483 570540

sales@metamark.co.uk
www.metamark.co.uk