

MetaGuard-i-UV

Performance PVC Overlamine for UV Prints



Product Description

MetaGuard MGI-UV is the matched overlamine for Metamark MD-I series, and for use with UV print technology. The specially formulated solvent-based adhesive gives a high bond to the low energy surface of UV inks, overcoming silvering. Overlaminating with MetaGuard MGI-UV provides increased resistance to abrasion and durability of the print and offers UV inhibitors. It can be used on flat or simple curves such as vehicle graphics. It is available in Gloss finish and has a Fire Rating of Class B [BS EN 13501-1:2007.] The unprinted film is durable up to 5 years outdoor.

Features & Benefits

- UK Manufactured.
- Matched to Metamark MDi Print films.
- MetaSure Warranty with 5 year durability.
- For use on UV prints.

Face Film

Face Film	Calendered PVC
Gauge (ISO 2286-3)	70 micron nominal ¹
Tensile Strength	50N/25mm MD / 48N/25mm TD nom
Elongation at break	180% MD nominal

Adhesive

Type	Permanent clear pressure sensitive solvent-based acrylic with UV inhibitors
Adhesion to glass 20 mins	17N/25mm nominal
Adhesion to glass 24 hour	23N/25mm nominal
Application temperature	+10°C to +50°C
Service temperature	-30°C to +100°C

Release Liner

Print	'Metamark Digital Vinyl' Grey print
Weight	140 gsm nominal
Type	Solventless Kraft

Finishes

Finishes Available	MG-i-UV-005	Gloss
	MG-i-UV-002	Matt

Roll Presentation

Roll Widths	1.37m / 1.60m
Roll Lengths	50m

Durability

Shelf Life	2 years. (10-20°C and 50% R.H).
External weathering	5 years (Unprinted). Northern European conditions, vertical. Refer to full Metamark International durability guide.
Fire Rating	Class B - BS EN 13501-1:2007
Chemical Resistance	The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oil gasoline, paraffin, hydraulic oil, ant-freeze, soap suds, etc.
Regulations	REACH and RoHS Compliant.

Handling and Application

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours (darker colours can be longer).
- Suitable for use on UV, Eco Solvent, Solvent and Latex prints.
- The product is matched to MDi. Matched laminates prevent tunnelling and delamination.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- The user should determine suitability of the overlamine to the print media.

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

- Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140
- Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk
www.metamark.co.uk